

# ChemGrout®

"Equipment for Grouting Since 1969"

805 E. 31st Street, P.O. Box 1140

LaGrange Park, Illinois 60526

Phone: 708-354-7112 Fax: 708-354-3881

## Material Testing Results

Date: 7/13/00

E-Mail: info@chemgrout.com

Web Site: www.chemgrout.com

**Manufacturer:** MAPEI  
1851 NW 22nd Street  
Fort Lauderdale, FL 33311

**Contact:** Kelly Page  
**Phone:** 954-485-8575  
**Fax:** 954-485-2032

**Material:** Novo/Plan M20

**Lot #** LO9E007

**Material Application:** Self leveling and repair mix. Extended healing time,  
fast setting very high compressive strength

**Mfg. Plant:** Not Available

**Std. Bag Weight** 55#

**Environmental Conditions:** Outside Temperature 86.5°F

Humidity 46%

**Equipment Used:** Model CG570  
Mixer Paddle

Pump 2TJ6 Progressing Cavity  
Power Hydraulic

**Mixing Water Temp:** 77 °F

**Batching Method:** Quantity Material 165 lbs.

Quantity Water 41 lbs

**Mixing Time:** 30-40 Seconds

**Batch Temp:** 88.2 °F

**Specific Gravity:** Material Weight 268 grams  
Water Weight 140 grams

SG = 1.91

**Flow Cone** 44 Seconds

**Sieve Analysis:** Weight Retained (grams) No. 4 No. 50  
No. 8 No. 100  
No. 16 No. 200  
No. 30 Pan

**Pumping Method:** Hose Dia. & Lengths used (one) 50' L x 1 1/4" I.D.  
Recirculated through hose, recorded pressures at various flow rates.

**Observations:** The material get thinner the longer it's mixed  
Very smooth creamy looking product  
40 minute plus healing time with primer put down

**Results:** ChemGrout rates the pumpability of this product as "Excellent" with a rating of "A". All ChemGrout models can mix and pump this material.

Mapei Novo Plan M20