

ChemGrout®

"Equipment for Grouting Since 1969"

805 E. 31st Street, P.O. Box 1140

LaGrange Park, Illinois 60526

Phone: 708-354-7112 Fax: 708-354-3881

Material Testing Results

Date: September 11, 2001

E-Mail: info@chemgrout.com

Web Site: www.chemgrout.com

Manufacturer:	Tamms 3835 State Route 72 Kirkland, IL 60146	Contact:	Brad Nemunaitis	
		Phone:	800-862-2667	
		Fax:	815-522-2323	
Material:	Tamoseal (Gray)	Lot #	143503	
Material Application:	Waterproofing material, cement based, spray applied			
Mfg. Plant:	Kirkland, IL	Std. Bag Weight:	50 #	
Testing Conditions:	Outside Temperature: 76.8°F	Humidity:	50%	
Equipment Used:	Model: CG570 Mixer: Paddle	Pump:	2TJ6 Progressing Cavity	
		Power:	Hydraulic	
Std. Mix Ratios:	one 50 lb bag to 8 quarts water	Water Temp:	61 °F	
Batching Method:	Quantity Material: 150 lbs.	Quantity Water:	48 lbs	
Mixing Time:	90 Seconds	Batch Temp:	69 °F	
Specific Gravity:	SG = 1.81	Flow Cone	28 Seconds	
Pumping Method:	Recirculated through hose, recorded pressures at various flow rates.			
Flow Rate/Pressure:	Flow Rate	Pressure	Flow Rate	Pressure
Hose (1 1/4" x 25')	2.15 GPM	0 PSI	23.60 GPM	20 PSI
Hose ()	4.52 GPM	10 PSI	GPM	PSI
Hose ()	6.67 GPM	10 PSI	GPM	PSI
Hose ()	8.82 GPM	20 PSI	GPM	PSI
Hose ()	10.59 GPM	20 PSI	GPM	PSI
Hose ()	12.95 GPM	20 PSI	GPM	PSI
Hose ()	15.00 GPM	20 PSI	GPM	PSI
Hose ()	17.20 GPM	20 PSI	GPM	PSI
Hose ()	19.14 GPM	20 PSI	GPM	PSI
Hose ()	21.34 GPM	20 PSI	GPM	PSI

Observations: Mixed easy, let batch sit for 5 minutes then started pumping again, no problems pumped easy, low discharge pressures, sprayed easy, use 1/4" tip Estimate maximum pumping distance over 200 feet at 20 GPM.

Results: ChemGrout, Inc. rates the pumpability of the product as a "9" out of 10, with 10 being the easiest. We recommend the 2C4 pump or higher